

Concrete Surface Finishes

Supplier	Brand
Texture Coatings of America, Inc. Ft. Lauderdale FL - Ft. Lauderdale, FL	Tex-Cote 300 Bridge Cote XL-70 bridge Cote
The Euclid Chemical Company Cleveland, OH	Tammscoat (fine texture)
The Sherwin-Williams Company San Antonio, TX	Concrete Texture Coating B97W155

The color shall be concrete gray, shade 36622 of the Federal Color Standard 595A.

Method of Documentation of Acceptance:

By brand and source.

Method of Approval:

- **The manufacturer will provide the Materials Division with the following:**
 - **Certified test results from a commercial, independent testing laboratory for freeze-thaw resistance,**
 - **Accelerated weathering,**
 - **Fungus growth resistance,**
 - **Chemical analysis of formulation, and physical properties.**

Freeze-thaw resistance, accelerated weathering, and fungus growth resistance testing shall be performed according to AHTD Test Method 806:

Freeze-Thaw Resistance - Cold storage at -0°F(-18°C) / Thawing at 60°F 80°F (16° C-27°C) for fifty (50) cycles. At the end of fifty cycles of the Freeze-Thaw test, the specimen shall show no visible defects.

Accelerated Weathering – Tested per ASTM G 153, Cycle 1 or ASTM 155, Cycle 1, for 5000 hrs. The specimen shall show no deleterious effects at 5000 hours when viewed under 5x magnification.

Fungus Growth Resistance – Minimum fungus resistance rating of 10 when tested according to Federal Specification TT-P-29 and ASTM D 3273 with twenty-one (21)

Concrete Surface Finishes

day minimum incubation period.

Retesting will be required whenever performance has been unsatisfactory or for a change in formulation.

- Sample(s) of the material along with an infrared spectra of the synthetic resin binder shall be furnished to the Materials Division for further testing and evaluation.
- When deemed necessary by the Materials Engineer, and at a frequency determined by him, random samples will be taken and may be tested for quality. Failure of these tests and/or unacceptable field performance as determined by the Department will be cause for removal of a product from this QPL.

No information contained in these lists is to be used for promotional purposes.

The manufacturer of privately labeled products must be disclosed.